



## TECHNICAL DATA SHEET

### ENCAP GLOSS 75 MICRON

#### Product Description

Bi-axially Oriented Polyester Film, Polyethylene Terephthalate (PET) - Encapsulation thermal film with **GLOSS** finish - Both side Corona treated - Low melt adhesive coating inside - Excellent optical properties and good resistance to scuff, scratch & tear

Typical Properties				
Property		Unit	Test Method	Value
Thickness		( $\mu\text{m}$ )		75
Yield		$\text{m}^2/\text{kg}$ .	ASTM D 4321	12.82
Unit Weight		$\text{g}/\text{m}^2$		78
Tensile Strength	MD	$\text{kg}/\text{mm}^2$	ASTM D882	6.4
	TD	$\text{kg}/\text{mm}^2$	ASTM D882	5.9
Elongation at Break	MD	%	ASTM D882	114
	TD	%	ASTM D882	129
Gloss Value	B			90.8
Haze		%	ASTM D1003	78.2
Wetting Tension	A + B	Dynes/cm	ASTM D 2578	42
Application Temperature	A	$^{\circ}\text{C}$		100-130
A: Adhesive Side B: Gloss Side				

**Disclaimer** - The above information is indicative only. The results shown are a general guide to the material properties which are subject to change and do not act as a guarantee.

Graphic Image Films Ltd.  
 Unit 5, Ridge Way, Crendon Industrial Park,  
 Long Crendon, Bucks, HP18 9BF.  
 T: 01844 208308, F: 01844 208608  
 Email: [info.gif@graphicimagefilms.co.uk](mailto:info.gif@graphicimagefilms.co.uk)  
[www.graphicimagefilms.co.uk](http://www.graphicimagefilms.co.uk)