



TECHNICAL DATA SHEET

WET SOFT TOUCH MATT 17 MICRON

Product Description

Bi-axially Oriented Polypropylene Film (BOPP) Wet lamination film with **SOFT TOUCH** finish - Smooth velvet feel with good antiscratch properties and excellent clarity by contact - No tonality lost after lamination - Corona treated

| Typical Properties | | | | | | |
|---------------------------------------|---|-----|--|------------------------|--------------|--|
| Graphic Image Films Wet Soft Touch | Property | | Unit | Test Method | Value | |
| | Thickness | | (μm) | ASTM E 252 | 17 | |
| | Yield | | m^2/kg . | ASTM D 4321 | 64,6 | |
| | | | In^2/Lb | | 45,449 | |
| | Unit Weight | | g/m^2 | Derprosa - 009 | 15,5 | |
| | Haze | | % | ASTM 1003 | 95 | |
| | Gloss | B | % | ASTM D 2457 60° | 4 | |
| | Tensile Strength at Break | MD | N/mm^2 Lb/In^2 | ASTM D 882 | 115 16,710 | |
| | | TD | | | 235 34,146 | |
| | Elongation at Break | MD | % | ASTM D 882 | 165 | |
| | | TD | | | 50 | |
| | Thermal Shrinkage | MD | % | ASTM D1204 120°C, 5min | 4 | |
| | | TD | | | 1,5 | |
| | Wetting Tension | B | Dynes/cm | ASTM D 2578 | >42 | |
| | | A | | | >37 | |
| | C.O.F Film/Film | B/B | | ASTM D 1894 | 0.45 | |
| | A: Inside B: Soft Touch Side MD: Machine Direction TD: Transverse Direction | | | | | |

Disclaimer - The above information is indicative only. The results shown are a general guide to the material properties which are subject to change and do not act as a guarantee.

Graphic Image Films Ltd.
 Unit 5, Ridge Way, Crendon Industrial Park,
 Long Crendon, Bucks, HP18 9BF.
T: 01844 208308, **F:** 01844 208608
Email: info.gif@graphicimagefilms.co.uk
www.graphicimagefilms.co.uk