



TECHNICAL DATA SHEET

THERMAL HOLOGRAPHIC METALISED 28 MICRON

Product Description

Bi-axially Oriented Polypropylene Film (BOPP) - Thermal lamination film with seamless **HOLOGRAPHIC** finish - Low melt adhesive coating inside.

Typical Properties						
GIF Supplies Thermal Metalised Holographic	Property		Unit	Test Method	Value	
	Thickness		(μm)	GB/T6672	28 \pm 5.0%	
	Yield		m ² /kg .	ASTM D 4321	38 \pm 5.0%	
	Average Grammage		g/m ²	Weight Basis	26.2 \pm 5.0%	
	Tensile Strength	MD		%	GB/T1040	210 \pm 5.0%
		TD				200 \pm 5.0%
	Elongation	MD		%	GB/T1040	100 \pm 5.0%
		TD				110 \pm 5.0%
	Optical Density			GB7974	2 \pm 5.0%	
	Surface Energy	BOPP		Dynes	GB/T14216	38
		EVA				42
	Application Temperature	A		°C		95-105
	Application Pressure			kg/cm ²		0.5-0.8mpa
	Application Speed			m/min		5-60m/min
	A: Adhesive Side					

Disclaimer - The above information is indicative only. The results shown are a general guide to the material properties which are subject to change and do not act as a guarantee.

Graphic Image Films Ltd.
 Unit 5, Ridge Way, Crendon Industrial Park,
 Long Crendon, Bucks, HP18 9BF.
 T: 01844 208308, F: 01844 208608
 Email: info@gifsupplies.co.uk
 www.gifsupplies.co.uk