



## TECHNICAL DATA SHEET

### THERMAL SILK 27 MICRON

#### Product Description

Bi-axially Oriented Polypropylene Film (BOPP) - Thermal lamination film with **SILK** finish - Both side Corona treated - Low melt adhesive coating inside - Excellent silky matt finish and good resistance to elongation and tear

Typical Properties					
GIF Supplies Thermal Silk	Property		Unit	Test Method	Value
	Thickness		( $\mu\text{m}$ )	ASTM E 252	27
	Yield		$\text{m}^2/\text{kg}$ .	ASTM D 4321	44,44
	Unit Weight		$\text{g}/\text{m}^2$		22,5
	Gloss	B	Gardner	ASTM D 2457 45°	17-21
	Wetting Tension	B	Dynes/cm	ASTM D 2578	40
		A			44
	Application Temperature	A	°C		100-120
	A: Adhesive Side B: Silk Side				

**Disclaimer** - The above information is indicative only. The results shown are a general guide to the material properties which are subject to change and do not act as a guarantee.

Graphic **Image** Films Ltd.  
 Unit 5, Ridge Way, Crendon Industrial Park,  
 Long Crendon, Bucks, HP18 9BF.  
**T:** 01844 208308, **F:** 01844 208608  
**Email:** [info@gifsupplies.co.uk](mailto:info@gifsupplies.co.uk)  
[www.gifsupplies.co.uk](http://www.gifsupplies.co.uk)