



TECHNICAL DATA SHEET

WET EMBOSSED PEARL 30 MICRON

Product Description

Bi-axially Oriented Polypropylene Film (BOPP) - Wet lamination film with **EMBOSSED PEARL** finish - Both side Corona treated - High initial tear resistance

Typical Properties				
Property		Unit	Test Method	Value
Thickness		(µm)		30
Yield		m ² /kg .		36
Unit Weight		g/m ²		27,3
Density		g/cm ³	DIN 53479	0,91
Wetting Tension	B	Dynes/cm	DIN 53364	38
	A			40
Tensile Strength	MD	N/mm ²	DIN 53455	170
	TD			170
Elongation at Break	MD	%	DIN 53455	75
	TD			75.0
Temperature Resistance		°C		-50/+130
A: Inside B: Outside MD: Machine Direction TD: Transverse Direction				

Disclaimer - The above information is indicative only. The results shown are a general guide to the material properties which are subject to change and do not act as a guarantee.

Graphic Image Films Ltd.
 Unit 5, Ridge Way, Crendon Industrial Park,
 Long Crendon, Bucks, HP18 9BF.
T: 01844 208308, F: 01844 208608
Email: info@gifsupplies.co.uk
www.gifsupplies.co.uk