



## TECHNICAL DATA SHEET

### WET SILK 15 MICRON

#### Product Description

Bi-axially Oriented Polypropylene Film (BOPP) - Wet lamination film with **SILK** finish - Both side Corona treated - Excellent silky matt finish - Good anti-static properties

Typical Properties				
Property		Unit	Test Method	Value
Thickness		( $\mu\text{m}$ )	ASTM E 252	15
Yield		$\text{m}^2/\text{kg}$ .	ASTM D 4321	75,76
Unit Weight		$\text{g}/\text{m}^2$		13,2
Gloss	B	Gardner	ASTM D 2457 45°	24-30
Wetting Tension	B	Dynes/cm	ASTM D 2578	40
	A			38
C.O.F Film/Film (Kinetic)	B/B		ASTM D 1894	0,45
Haze		%	ASTM D 1003	30-38
Tensile Strength	MD	$\text{kg}/\text{cm}^2$	ASTM D 882	1100-1300
	TD			2400-2700
Elongation at Break	MD	%	ASTM D 882	140-180
	TD			40-60
Heat Shrinkage (120°C, 5min)	MD	%	ASTM D 1204	3,0-5,0
	TD			1,0-3,0
A: Inside B: Silk Side MD: Machine Direction TD: Transverse Direction				

**Disclaimer** - The above information is indicative only. The results shown are a general guide to the material properties which are subject to change and do not act as a guarantee.

Graphic Image Films Ltd.  
 Unit 5, Ridge Way, Crendon Industrial Park,  
 Long Crendon, Bucks, HP18 9BF.  
 T: 01844 208308, F: 01844 208608  
 Email: [info@gifsupplies.co.uk](mailto:info@gifsupplies.co.uk)  
[www.gifsupplies.co.uk](http://www.gifsupplies.co.uk)